


Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (original) A chemically amplified photosensitive resin composition comprising (A) an alkali-soluble novolak resin, (B) a resin or compound which in itself is insoluble or slightly soluble in alkali, but becomes soluble in alkali by the action of an acid, (C) an acid generating agent and (D) a photosensitizing agent containing a quinonediazide group.

2. (original) A chemically amplified photosensitive resin composition according to Claim 1, wherein said resin or compound which is itself insoluble or slightly soluble in alkali, but becomes soluble in alkali by the action of an acid has a structural unit represented by the general formula (I):



wherein R represents a saturated alkyl group having 1 to 20 carbon atoms and n is an integer from 1 to 10.

3. (currently amended) A chemically amplified photosensitive resin composition according to Claim 1 [[or 2]], which further comprises (E) an alkali-soluble acrylic resin.

4. (original) A chemically amplified photosensitive resin composition according to Claim 3, wherein said alkali-soluble acrylic resin contains a structural unit derived from

a (meth)acrylic acid, a structural unit derived from an alkylmethacrylate and, as required, a structural unit derived from styrene.

5. (currently amended) A chemically amplified photosensitive resin composition according to Claim 3 [[or 4]], wherein said alkali-soluble acrylic resin contains a structural unit derived from a hydroxyalkylmethacrylate, a structural unit derived from an alkylmethacrylate and, as required, a structural unit derived from styrene.

6. (currently amended) A chemically amplified photosensitive resin composition according to ~~any one of Claims 1 to 5~~ Claim 1, which further comprises (F) a compound containing at least two vinyloxyalkylester groups.

7. (currently amended) A chemically amplified photosensitive resin composition according to ~~any one of Claims 1 to 6~~ Claim 1, wherein the ratio by weight of said components (A) : (B) : (C) : (D) : (E) : (F) is 100 : 1 to 50 : 0.02 to 10 : 1 to 30 : 0 to 200 : 0 to 30.

8. (currently amended) A chemically amplified photosensitive resin composition according ~~any one of Claims 1 to 7~~ Claim 1, the composition being used in a layer thickness of 10 μ m or more.

9. (new) A chemically amplified photosensitive resin composition according to Claim 2, which further comprises (E) an alkali-soluble acrylic resin.

10. (new) A chemically amplified photosensitive resin composition according to Claim 9, wherein said alkali-soluble acrylic resin contains a structural unit derived from a

Serial No. To be Assigned
Filed: April 10, 2006

(meth)acrylic acid, a structural unit derived from an alkylmethacrylate and, as required, a structural unit derived from styrene.

11. (new) A chemically amplified photosensitive resin composition according to Claim 4, wherein said alkali-soluble acrylic resin contains a structural unit derived from a hydroxyalkylmethacrylate, a structural unit derived from an alkylmethacrylate and, as required, a structural unit derived from styrene.

12. (new) A chemically amplified photosensitive resin composition according to Claim 2, which further comprises (F) a compound containing at least two vinyloxyalkylester groups.

13. (new) A chemically amplified photosensitive resin composition according to Claim 3, which further comprises (F) a compound containing at least two vinyloxyalkylester groups.

14. (new) A chemically amplified photosensitive resin composition according to Claim 4, which further comprises (F) a compound containing at least two vinyloxyalkylester groups.

15. (new) A chemically amplified photosensitive resin composition according to Claim 5, which further comprises (F) a compound containing at least two vinyloxyalkylester groups.

16. (new) A chemically amplified photosensitive resin composition according to Claim 2, wherein the ratio by weight of said components (A) : (B) : (C) : (D) : (E) : (F) is 100 : 1 to 50 : 0.02 to 10 : 1 to 30 : 0 to 200 : 0 to 30.

EXPRESS MAIL MAILING LABEL NO. EV 689560155 US

Serial No. To be Assigned
Filed: April 10, 2006

17. (new) A chemically amplified photosensitive resin composition according to Claim 3, wherein the ratio by weight of said components (A) : (B) : (C) : (D) : (E) : (F) is 100 : 1 to 50 : 0.02 to 10 : 1 to 30 : 0 to 200 : 0 to 30.

18. (new) A chemically amplified photosensitive resin composition according to Claim 4, wherein the ratio by weight of said components (A) : (B) : (C) : (D) : (E) : (F) is 100 : 1 to 50 : 0.02 to 10 : 1 to 30 : 0 to 200 : 0 to 30.

19. (new) A chemically amplified photosensitive resin composition according to Claim 5, wherein the ratio by weight of said components (A) : (B) : (C) : (D) : (E) : (F) is 100 : 1 to 50 : 0.02 to 10 : 1 to 30 : 0 to 200 : 0 to 30.

20. (new) A chemically amplified photosensitive resin composition according to Claim 6, wherein the ratio by weight of said components (A) : (B) : (C) : (D) : (E) : (F) is 100 : 1 to 50 : 0.02 to 10 : 1 to 30 : 0 to 200 : 0 to 30.